



JL3305-2018/1



中国认可  
国际互认  
检测  
TESTING  
CNAS L7531

# Test Report

Report No.: 2019318000  
Anti-fake: 51C671CC

Date: 2019/10/16  
Page: 1/3

Client: Handan Yidao Metal Products Co., Ltd  
Address: No.183 Lianfang East Road, Handan, Hebei China  
Product: Dia.36mm Thread bar grade 930  
Dimension: D36×700 mm  
Quantity: 1PC  
Grade: —  
Material: Grade 930

*The information above is provided by the client. Our laboratory is not responsible for its authenticity.*

Sample Source: Supplied by client  
Sample Description: Integrity, black.  
Receiving Date: 2019-10-08  
Test Date: 2019-10-12~2019-10-16

### Specification & Conformance Requirement:

The technical requirement supplied by client.

Test Result: See next page

Zhejiang Guojian Testing Technology Co., Ltd.  
China National Center for Quality Test of Standard Parts (Zhejiang)

Approved by: *Zhang Dongchun*  
检验检测专用章

**Declaration:** 1. This test report shall be invalid if without the laboratory testing seal or signatures of authorized signatory. 2. This test report shall be invalid if altered. 3. Our laboratory is only responsible for the original report. Copying, faxing, photocopying versions of the report is only for reference purpose. 4. This report is invalid if parted. 5. This test report shall not be reproduced except in full without the written approval of the laboratory. 6. This report is responsible for designated samples only. 7. Any objection of the test result should be declared timely. The tested samples will be kept for 45 days. 8. If tested samples are returned or expired, retest will no longer be offered. 9. The last digit of the report number is the version number, the original number is "0". The version number increased when this report revised, meanwhile the original report invalid, the changed information is identified in bold font. 10. If the uncertainty is not given in this report, the decision rule is simple acceptance.

No.211, Yanbei Road, Haiyan, Zhejiang, China TEL:0573-86161256 86161587 FAX: 0573-86180133 Report check: <http://www.chinazbj.com>



# Test Report

Report No.: 2019318000

Page: 2/3

Test Item	Test Method	Requirement	Result	Conclusion
Tensile strength $R_m$ /MPa	GB/T 228.1-2010	$\geq 1080$	1198	Pass
Yield strength $R_{p0.2}$ /MPa	GB/T 228.1-2010	$\geq 930$	1128	Pass
Elongation A/ $5d_0$ /%	GB/T 228.1-2010	$\geq 6$	8.5	Pass
Elongation Agt/%	GB/T 28900-2012	$\geq 3.5$	3.5	Pass

 Reviewed by: *Tang Haisheng*

Test Item	Test Method	Requirement	Result	Conclusion
P/%	GB/T 4336-2016	$\leq 0.035$	0.014	Pass
S/%	GB/T 4336-2016	$\leq 0.035$	$< 0.008$	Pass

 Reviewed by: *Hu Shenhui*


201931800-Chemical analysis-Before testing



201931800-Chemical analysis-Testing




# Test Report

Report No.: 2019318000


Page: 3/3



201931800-Chemical analysis-After testing



201931800-Tensile test-curve



201931800-Tensile test-Before testing



201931800-Tensile test-Testing



201931800-Tensile test-After testing

