

Test Report

Date: 2022/01/13

Report No.: 2022007220

Page : 1/2

Client: HandanYidao Metal Products Co.,Ltd
Address: No.183 Lianfang East Road,Handan,Hebei China
Product: Thread Bar
Dimension: Dia.25mm
Quantity: 1pc
Grade: Grade500
Material: _____

The information above is provided by the client. Our laboratory is not responsible for its authenticity.

Sample Source: Supplied by client
Sample Description: See sample photos
Receiving Date: 2022-01-07
Test Date: 2022-01-13

Specification & Conformance Requirement :

Test Result: See next page



扫码查真伪



微信客服

Zhejiang Guojian Testing Technology Co.,Ltd.

Declaration: 1. This test report shall be invalid if without the laboratory testing seal or signatures of authorized signatory. 2.This test report shall be invalid if altered. 3. Our laboratory is only responsible for the original report. Copying, faxing, photocopying versions of the report is only for reference purpose. 4. This report is invalid if parted. 5. This test report shall not be reproduced except in full without the written approval of the laboratory. 6. This report is responsible for designated samples only. 7. Any objection of the test result should be declared timely. The tested samples will be kept for 45 days. 8. If tested samples are returned or expired, retest will no longer be offered. 9. The last digit of the report number is the version number, the original number is "0". The version number increased when this report revised, meanwhile the original report invalid, the changed information is identified in bold font.10.If the uncertainty is not given in this report, the decision rule is sim

No.777, Fengtan Road, Haiyan, Jiaxing, Zhejiang, China TEL:0573-86161256 86161587 Official website: <http://www.chinazhj.com>

Test Report



Report No. : 2022007220

Page : 2/2

Test Item	Test Method	Requirement	Result	Conclusion
Tensile strength R_m /MPa	GB/T 20065-2016	—	785	—
Yield strength $R_{p0.2}$ /MPa	GB/T 20065-2016	—	625	—
Percentage total extension at maximum force A_{gt} /%	GB/T 20065-2016	—	14.5	—
Elongation $A/10d_0$ /%	GB/T 20065-2016	—	18	—

Reviewed by : *Gu Longhua*

Approved by : *Li Bo*

 <p>202200722 Tensile test—stress-strain curve</p>	 <p>202200722-After test</p>
--	---

 <p>Sample photos</p>
--

REPORT FINALIZED

